

Substitutions for Pd

Threshold $N_{AB} > 9$

% of Pd substitutions
Absolute number of compounds with substitution



H	% of Pd substitutions Absolute number of compounds with substitution																He						
Li	Be																	B	C	N	O	F	Ne
Na	Mg 0.9 14	0	10	20	30	40	50	Al 1.7 26	Si 1.0 16	P	S	Cl	Ar										
K	Ca	Sc	Ti 0.8 12	V	Cr 2.0 31	Mn 2.9 43	Fe 3.8 57	Co 6.0 89	Ni 14.8 219	Cu 7.9 118	Zn 1.4 22	Ga 1.7 26	Ge 1.6 25	As	Se	Br	Kr						
Rb	Sr	Y	Zr	Nb	Mo	Tc	Ru 3.5 53	Rh 10.3 153	Pd	Ag 3.0 45	Cd	In 1.7 26	Sn 1.9 29	Sb	Te	I	Xe						
Cs	Ba		Hf	Ta	W	Re	Os 1.8 27	Ir 4.3 65	Pt 15.0 223	Au 6.4 95	Hg 0.6 10	Tl 1.6 24	Pb 1.4 21	Bi	Po	At	Rn						
Fr	Ra																						
		La	Ce	Pr 0.6 10	Nd	Pm	Sm	Eu	Gd	Tb	Dy	Ho	Er	Tm	Yb	Lu							
		Ac	Th	Pa	U	Np	Pu	Am	Cm	Bk	Cf	Es	Fm	Md	No	Lr							